

CARACTERÍSTICAS TÍPICAS TEST LINER M20

Fecha de revisión 12.12.07

UNE/EN/ISO-536	Gramaje	g/m ²	70	80	85	90	100	105	110	120	170	200	300	-
UNE/EN-20287	Humedad	%	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	+/- 1,5
UNE-57059	Indice Mullen (kPa m ² /g)x10		24.0	25.0	25.0	26.5	26.0	25.5	25.0	24.5	22.0	20.0	17.0	- 10%
ISO-9895	Indice SCT.ST	Nm/g	15	15	15	15	15	15	15	15	15	15	15	- 10%

UNE/EN-20187	ACONDICIONAMIENTO DE MUESTRAS			
	Humedad relativa	%	50.0	+/-2%
	Temperatura	°C	23.0	+/-1°C

OBSERVACIONES:

- Para gramajes distintos a los nominales indicados se aplicarán los valores del gramaje inmediatamente superior.
- La tolerancia de +/- 4% hasta 100g/m², de +/-3% hasta 224g/m², de +/-5% para los superiores.



Imprimir